



X Panel Eucalyptus B/BB

Specifications

Species	100 % Eucalyptus spp.
Resin	Phenolic
Face veneer Quality	B/BB
Face veneers thickness (after sanding)	~ 1 mm
Face veneer type	Full sheet, no repairs allowed
Face veneer direction	Long grain
Backing veneer thickness	~1,5 mm
Backing Veneer type	smooth repairs allowed
Interior veneer thickness	~1,5 mm
Interior veneer Quality	C
Sanding	120 grit
Size	1220 x 2440 / 1120 x 2500 / 1250 x 2500
Tolerance size	+/- 2mm
Tolerance thickness	+/- 0,5 mm
FSC certificate	Yes
CE 4 marking	Yes
Bonding Quality	WBP / EN 363-3 Exterior applications
Formaldehyde	E1

Composition

Final product	Number of layers	Composition
9 mm	7	7 x ~ 1.5 mm
12 mm	9	9 x ~ 1.5 mm
15 mm	11	11 x ~ 1.5 mm
18 mm	13	13 x ~ 1.5 mm
21 mm	15	15 x ~ 1.5 mm
24 mm	17	17 x ~ 1.5 mm
27 mm	19	19 x ~ 1.5 mm

Delivery ~ 10 weeks after confirmed written order.

contact@XylemTrading.com

Xpanel Eucalyptus

Hèt duurzame alternatief voor berken multiplex